























TECHNICAL CHARACTERISTICS

wineo 400

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582

wineo

	wineo 400 wood	wineo 400 wood XL	wineo 400 stone		
Format	1200 x 180 mm	1505 x 235 mm	609.6 x 304.8 mm		
Product thickness	2 mm	2 mm	2 mm		
Planks, tiles / m² per box	18 / 3.89 m ²	12 / 4.24 m ²	18 / 3.34 m ²		
Boxes / m² per pallet	60 / 233.40 m ²	64 / 271.36 m ²	60 / 200.40 m ²		
Guarantee Extended warranty	15 years for private use according to Windmüller warranty conditions - www.wineo.de + 5 years for laying on PU underlay mat				
Classification				Product composition	
 Utilization class 23 EN ISO 10874	Domestic area with intensive usage		1	Surface seal	
 Utilization class 31 EN ISO 10874	Commercial sector with low or occasional usage		2	Surface texture Various embossings	
Wear layer binder content EN ISO 10582	Typ I		3	Wear layer Thickness 0.3 mm	
 R9 Anti slip category DIN 51130	R 9		4	Design Decor film	
 Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time		5	Base layer	
 Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6		6	Backing	
 Residual indentation EN ISO 24343-1	≤ 0.1 mm without underlay mat ~ 0.17 mm with silentPREMIUM		7	Underlay material silentPLUS (available separately)	
 Thermal resistance EN 12667	0.011 (m ² K)/W without underlay mat 0.021 (m ² K)/W with silentPREMIUM or silentPLUS			wood bevelled edge - 4-sides bevelled edge	
 Impact sound reduction EN ISO 16251-1	~ 4 dB without underlay mat ~ 17 dB with silentPLUS			wood XL registered embossed surface, bevelled edge - 4-sides	
 Dimensional stability EN ISO 23999	~ 0.15 %		 70 710 4061-6 www.proficert.com 		
REACH	free from SVHC substances ≥ 0.1 %				
Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203				
 Windmüller GmbH Nord-West-Ring 21 D-32832 Augustdorf - 18 - DOP: 0301010 EN 14041:2004 / AC2006 1658      www.wineo.de		 Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (tres faibles émissions)		 	

Relevant information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.